

IN THE CLAIMS

Claims 2 and 17 are cancelled, and claims 29-46 were previously withdrawn, as directed to a non-elected invention. Please amend claims 1, 3-16, and 18-28 to the following:

1. (Currently Amended) A method comprising:
dispersing zeolite particles in a liquid sol to form a zeolite – sol colloid;
depositing the zeolite – sol colloid on an underlying layer; and
extracting ~~at least some~~ a first amount of the liquid from the zeolite – sol colloid to form a
wet gel – zeolite composite, wherein the first amount of the liquid is in the range of
five to ninety-five percent of the liquid.
2. (Cancelled)
3. (Currently Amended) The method of claim 2, wherein extracting ~~at least some~~ a first
amount of the liquid comprises:
drying the zeolite – sol colloid.
4. (Original) The method of claim 3, wherein drying the zeolite – sol colloid comprises:
oxidizing the zeolite – sol colloid.
5. (Currently Amended) The method of claim 2, wherein extracting ~~at least some~~ a first
amount of the liquid comprises:
vacuuming the liquid out of the zeolite – sol colloid.

6. (Currently Amended) The method of claim 2, wherein extracting ~~at least some~~ a first amount of the liquid comprises:
heating the zeolite – sol colloid.
7. (Original) The method of claim 6, wherein the zeolite – sol colloid is heated under a vacuum.
8. (Original) The method of claim 1, further comprising:
calcinating the wet gel – zeolite composite.
9. (Original) The method of claim 8, wherein calcinating the wet gel – zeolite composite comprises:
heating the wet gel – zeolite composite; and
cooling the wet gel – zeolite composite.
10. (Original) The method of claim 9, wherein the wet gel – zeolite composite is heated under a vacuum.
11. (Original) The method of claim 8, wherein calcinating the wet gel – zeolite composite to form a composite gel-zeolite dielectric layer comprises: oxidizing the wet gel – zeolite composite.

12. (Currently Amended) The method of claim 2 1, further comprising:

etching at least a via and a trench in wet gel – zeolite composite film;

forming a conductive material in at least the via and the trench; and

forming the wet gel – zeolite composite into an aerogel – zeolite composite, after

forming the conductive material in at least the via and the trench.

13. (Original) The method of claim 12, wherein forming the wet gel – zeolite composite into

an aerogel – zeolite composite comprises extracting approximately all of the remaining

liquid from the wet gel – zeolite composite.

14. (Original) The method of claim 13, further comprising calcinating the aerogel – zeolite

composite.

15. (Original) The method of claim 1, wherein dispersing the zeolite particles in the liquid

sol comprises:

stirring a first amount of zeolite into the liquid sol.

16. (Currently Amended) The method of claim 15, wherein the first amount of zeolite is a

molar percentage of the zeolite – sol colloid, the molar percentage of zeolite being in the

range of one to fifty percent.

17. (Cancelled)

18. (Original) The method of claim 1, wherein the sol is a silica sol.
19. (Original) The method of claim 1, wherein the sol comprises an alcohol.
20. (Original) The method of claim 19, wherein the alcohol is selected from the group consisting of ethanol, methanol, 1- or 2-propanol, or 1-butanol.
21. (Original) The method of claim 19, wherein the sol further comprises an acid.
22. (Original) The method of claim 21, wherein the acid is selected from a group consisting of hydrochloric (HCl), nitric, sulfuric, phosphoric, hydrofluoric (HF), acetic, or citric acid.
23. (Original) The method of claim 21, wherein the sol further comprises a silicon precursor.
24. (Original) The method of claim 23, wherein the silicon precursor is selected from a group consisting of tetraethoxysilane (TEOS), tetramethoxysilane (TMOS), tetrapropoxysilane (TPOS), and tetrabutoxysilane (TBOS).
25. (Original) The method of claim 23, wherein the sol further comprises a surfactant.

26. (Original) The method of claim 25, wherein the surfactant is selected from a group consisting of hydrochloric (HCl), nitric, sulfuric, phosphoric, hydrofluoric (HF), acetic, or citric acid.
27. (Original) The method of claim 1, wherein depositing the zeolite – sol colloid comprises: spin-coating the zeolite – sol colloid on the underlying layer.
28. (Original) The method of claim 1, wherein depositing the zeolite – sol colloid comprises: dip-coating the zeolite – sol colloid on the underlying layer.
29. (Withdrawn) A method of forming a layer in an interconnect structure comprising:
- mixing a solution with at least a silicon precursor, a alcohol base, zeolite and water;
 - depositing the solution on an underlying layer;
 - gelling the solution into a wet gel; and
 - calcinating the wet gel.
30. (Withdrawn) The method of claim 29, wherein depositing the solution comprises dip-coating the underlying layer in the solution.
31. (Withdrawn) The method of claim 29, wherein depositing the solution comprises spin-coating the solution onto the underlying layer.

32. (Withdrawn) The method of claim 29, wherein gelling the solution into a wet gel comprises extracting at least some of the solution.
33. (Withdrawn) The method of claim 32, wherein extracting at least some of the solution comprises oxidizing the solution.
34. (Withdrawn) The method of claim 32, wherein extracting at least some of the solution comprises heating the solution.
35. (Withdrawn) The method of claim 29, wherein calcinating the wet gel comprises:
heating the wet gel; and
cooling the wet gel.
36. (Withdrawn) A method comprising:
forming an etch stop on an underlying layer;
spin-coating a liquid sol - zeolite colloid on the underlying layer;
extracting approximately all of the liquid from the liquid sol - zeolite colloid to form an aerogel - zeolite composite film;
etching at least a via and a trench in the aerogel - zeolite composite film; and
forming a conductive material in at least the via and the trench.
37. (Withdrawn) The method of claim 36, wherein extracting approximately all of the liquid from the liquid sol - zeolite colloid comprises: oxidizing the sol - zeolite colloid.

38. (Withdrawn) The method of claim 36, wherein extracting approximately all of the liquid from the liquid sol – zeolite colloid comprises: heating the sol – zeolite colloid.
39. (Withdrawn) The method of claim 36, wherein the liquid sol is a silica based sol.
40. (Withdrawn) An interconnect structure comprising:
at least one via opening and one trench defined by a gel – zeolite composite dielectric, which is disposed above an underlying layer;
a barrier layer disposed on the surfaces of the gel-zeolite composite dielectric; and
a conductive layer disposed on the barrier layer.
41. (Withdrawn) The interconnect structure of claim 40, wherein the gel-zeolite composite dielectric is a wet gel – zeolite composite dielectric.
42. (Withdrawn) The interconnect structure of claim 40, wherein the gel-zeolite composite dielectric is an aerogel – zeolite composite dielectric.
43. (Withdrawn) The interconnect structure of claim 40, wherein the gel-zeolite composite dielectric is a calcinated gel – zeolite composite dielectric.
44. (Withdrawn) The interconnect structure of claim 40, wherein the etch-stop is comprised of silicon nitride.